

Larisplast LP 232

Meets the Israeli standards # 896

<p>Retarder water reducing plasticising admixture for concrete. Produces workable, sealed and durable concrete. Without chlorides.</p>	<p><u>Dosage:</u> 0.6%-1.2% from the cement weight including PFA or microsilica. Possible to use different dosages for special works, but then it requires preliminary experience. Dosage to be adjusted in cold weather to prevent excessive setting of the concrete.</p>
<p><u>Description:</u> LP 232 is water reducing admixture based on improved composite lignosulphonat.</p>	<p><u>Specific data:</u> Thin, brown color. SPECIFIC GRAVITY: 1.1 (± 0.05) at 20° C. PH: 8 (± 1.5).</p>
<p><u>Advantages:</u> LP 232 improves the characters of fresh and hard concrete. Higher workability and easy to pour also in high temperatures. Longer workability period. Increase the strength of the concrete. Simplify and expedite the concrete pumping. Higher final strength. Longer life and higher degree of sealing. Improved architectural concrete. Better concrete finishing.</p>	<p><u>Instruction for use:</u> LP 232 add only after adding 50%-70% of water. Do not add the admixture to dry aggregates. Mix until the concrete is homogenous.</p>
<p><u>Durability and impermeability:</u> Based on the water/cement ratio, concrete becomes more dense, less porous, and harder to penetrate. Thus, there is less penetration of aggregates and the concrete is more durable.</p>	<p><u>Packaging:</u> In 1,000 liter containers.</p>
<p><u>Use:</u> Recommended for all types of concrete. Lowering the water/cement ratio. Recommended for long distance</p>	<p><u>Storage:</u> Length of storage not to exceed 12 months. Store in temperature of + 5° to + 30° C. The freezing point is approx -1° C.</p>

13 Habonim st Kiriat Gat 8211202 ISRAEL
Tel:972-8-6204040 , Fax:972-8-6460321
E-mail:Stella@larisplast.com

LarisPLAST Ltd.

ADVANCED PRODUCTS FOR CONCRETE AND BUILDING

<p>transportation of ready mix concrete. Holds concrete workability for longer period in warm weather. Increases the pumping power of the concrete.</p> <p><u>Suitable:</u> For all type of work with cement. For all type ordinary Portland cement and with addition of PFA or microsilica.</p>	<p><u>Safety:</u> LP 232 is not defined as dangerous material. Avoid direct contact with skin and eyes. Use gloves. In case of contact with the material wash immediately with plenty of water and seek medical advice. Not for eating.</p> <p><u>Fire:</u> LP 232 is based on water and is not flammable.</p>
---	--

For additional information, please contact Larisplast.

13 Habonim st Kiriat Gat 8211202 ISRAEL
Tel:972-8-6204040 , Fax:972-8-6460321
E-mail:Stella@larisplast.com

www.larisplast.com